


IN THE CLAIMS:



Cancel claims 6 and 7 without prejudice.

Claims 5, 8, and 9 are amended as follows:

RECEIVED
OCT 19 2001
TC 1700

B/
sh
DI
--5. (Amended) A method for determining and controlling the material flow of

continuous-cast slabs in a continuous casting installation by monitoring and optimizing the
temperature on the transport path of the continuous-cast slabs between the continuous-casting
installation and a rolling mill, said method comprising the steps of:

a. determining a temperature of the liquid phase of the continuous-cast slab at a
mold exit of the continuous-casting installation and physical parameters of the continuous-cast slab
including temperature-dependent material values comprising at least one of density ρ , specific heat
 C_p , thermal conductivity λ , and scale properties;

b. determining an amount of heat and a temperature profile of the continuous-
cast slab by calculating the convective mixing of the amount of heat contained in the continuous-
cast slab and the time-dependent heat loss from the inhomogenously cooling of the continuous-cast
slab, wherein the step of calculating comprises using a mathematical-physical model calculated
using one of a two-dimensional finite element method, a finite difference method, and software
using formulas derived from off-line studies; and

c. controlling the material flow in the continuous-casting installation via a slab-
monitoring system of the continuous-casting installation and using the amount of heat and the
temperature profile determined in said step b. as an input to the slab-monitoring system.--

132
sub
P2

--8. (Amended) The method of claim 5, wherein said step a. further comprises determining a surface temperature of the continuous-cast slab, said step c. comprises using a surface temperature of the continuous-cast slab determined in said step a. as an input to the slab monitoring system, and said step c. further comprises automatically controlling the material flow via the slab monitoring system based on the amount of heat and the temperature profile determined in said step b. and the surface temperature of the continuous-cast slab.--

--9. (Amended) The method of claim 5, wherein said step a. further comprises determining a surface temperature of the continuous-cast slab and said step c. further comprises using the surface temperature of the continuous cast slab measured in said step a. as an input to the slab monitoring system.--